

## Rheological additive for aqueous systems - High efficiency with low concentration -

**Sepiogel TX** imparts excellent thixotropic and pseudoplastic properties to the systems in which it is incorporated, reducing segregation and thickening the system.

Typical values Chemical composition	Sepiolite Hydrous mag	gnesium silicate
Colour Appearance	light cream fine powder	
Moisture pH-value (6% distilled water) Bulk density	% g/l	< 18 10.3 570
Particle size distribution, dry sieving  Particle size distribution, wet sieving	> 44 µm	14 %
Sieve residue	> 44 µm	5,6 %
<u>Packaging</u>	22 kg bags, 3	6 bags/pallet = 792 kg

All information in this publication are in accordance with our present experience and knowledge. As we have no influence on the processing and application of our products the user is solely responsible for examining their suitability. Current patents, laws and regulations are to be observed.

Shelf life

January 2019

Consume best before 1 year from

manufacturing date